

PRODUCT DESCRIPTION

DATE: 3/1/2005 REVISION: 2

CALCIUM CARBIDE: QUARTER ($\frac{1}{4}$ " X $\frac{1}{12}$ ")

GAS YIELD (Percent CaC_2 ; Cubic Feet Acetylene/Pound):

Minimum Purity / Gas Yield: 73.7% / 4.40 cft./#

SIZING:

Pass through 0.3125" (7.9 mm.) 100% Minimum

Pass through 0.055" (1.4 mm. / 14 mesh U.S.) 5% Maximum

ANALYSIS BASIS: Sampling, analysis, and reporting shall represent average properties of individual shipment lots.

AVAILABLE WITH OIL TREATMENT